


Uni-Gard™ Technical Data Sheet

UG925

Revision: UG925-12182019

Product	UG925																			
Scope	One piece foam backed induction liner that features an easily opened clean peel on glass containers																			
Composition	<table border="1"> <thead> <tr> <th>Material</th> <th>Standard</th> <th>Metric</th> </tr> </thead> <tbody> <tr> <td>PET Film</td> <td>0.00047"</td> <td>0.012mm</td> </tr> <tr> <td>Polyolefin Foam</td> <td>0.0045"</td> <td>0.114mm</td> </tr> <tr> <td>PET Film</td> <td>0.00047"</td> <td>0.012mm</td> </tr> <tr> <td>Foil</td> <td>0.00079"</td> <td>0.020mm</td> </tr> <tr> <td>Heat Seal</td> <td>35gsm (weight)</td> <td>35gsm (weight)</td> </tr> </tbody> </table>	Material	Standard	Metric	PET Film	0.00047"	0.012mm	Polyolefin Foam	0.0045"	0.114mm	PET Film	0.00047"	0.012mm	Foil	0.00079"	0.020mm	Heat Seal	35gsm (weight)	35gsm (weight)	
Material	Standard	Metric																		
PET Film	0.00047"	0.012mm																		
Polyolefin Foam	0.0045"	0.114mm																		
PET Film	0.00047"	0.012mm																		
Foil	0.00079"	0.020mm																		
Heat Seal	35gsm (weight)	35gsm (weight)																		
Adhesive or resin bonding layers not shown.																				
FDA Status: 21 CFR 177.1210	Recommended Storage and Handling: Refer to website																			
Drug Master File (DMF):	EU / EP Reg.: 10/2011/EC																			
GTR Oxygen: Essentially zero	MVTR: Essentially zero																			
Sealing to glass containers: Selig can not guarantee the performance or seal integrity of this materials when applied to any glass (treated or untreated) container. We suggest you contact your glass supplier for recommendations on glass treatments that may or may not improve performance or seal integrity.																				
Print Location (if any):																				

Selig materials are compliant with limitation of heavy metals in packaging per CONEG & EU 94/62/EC, article 11.

MSDS's are not required as Selig is not a chemical manufacturer or distributor and our products are 'articles' intended for food packaging per 29 CFR 1910.1200 (HazCom).

The information contained within this product data bulletin is to be used as a general guide in determining which structures are offered for sealing to specific container materials. All of the information which we provide is reliable to the best of our knowledge, but the accuracy thereof is not guaranteed. We suggest that consumers determine suitability for their own application.

www.seligsealing.com

Corporate Headquarters
Selig Sealing Products, Inc.
342 E Wabash St
Forrest, IL 61741, USA
Phone: +1 (815) 785-2100
Fax: +1 (815) 657-7584

North American Sales
Selig Sealing Products, Inc.
184 Shuman Blvd., Suite 310
Naperville, IL 60563, USA
Phone: +1 (630) 922-3158
Fax: +1 (630) 922-8469

European Sales and Manufacturing
Selig UK, LTD 635-637 Ajax Avenue
Slough Trading Estate
Slough Berkshire SL14BH UK
Phone: +44 (0) 1753 773 000
Fax: +44 (0) 1753 773 111

Canadian Manufacturing
Selig Canada, ULC
145 Edward Street
Aurora, Ontario Canada, L4G 1W3
Phone: +1 (905) 727-0114
Fax: +1 (905) 727-8544

Swiss Manufacturing
Selig Switzerland LTD
Bahnhofstrasse 11
CH-8172 Niederglatt
Phone: +41 (0) 44 851 50 50
Fax: +41 (0) 44 851 50 51